

CASING TECHNICAL DATA SHEET

4.5 x 0.337 EPL80 Long Round

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

TDS Date (MM/DD/YY)

1-20-25	

1D3 Date (MM/DD/11) 1-20-23			
PIPE BODY DATA	Unit	Imperial	Metric
Nominal Outside Diameter	in	4.500	114.30
Nominal Wall Thickness	in	0.337	8.56
Remaining Body Wall (RBW)		95.0%	95.0%
Type of Thread		Long Round	Long Round
Grade		EPL80	EPL80
Coupling Type		11th Edition	11th Edition
Label Weight		15.10	15.10
Plain End Weight	lb/ft	15.00	22.32
Pipe Minimum Yield	ksi	82	565
Pipe Maximum Yield	ksi	95	655
Pipe Minimum Tensile	ksi	95	655
Standard Drift Diameter (min)	in	3.701	94.00
Alternate Drift Diameter (min)	in	N/A	N/A
Pipe Body Plain End Yield	1b	361,000	163,750
Pipe Body Internal Yield	psi	11,670	80,460
Collapse Pressure - Standard	psi	N/A	N/A
Collapse Pressure - High	psi	11,990	82,670
CONNECTION DATA			
Coupling Minimum Yield	ksi	80	552
Coupling Maximum Yield	ksi	95	655
Coupling Minimum Tensile	ksi	95	655
Coupling or Joint Outside Diameter (nom)	in	5.250	133.35
Coupling Thread Fracture Strength	lb	622,000	282,130
Pipe Thread Fracture Strength	1b	308,000	139,710
Pull Out Strength	lb	330,000	149,690
Nominal Make-Up Torque or Make-up Torque Range	ft-lb	3,300	4,470
Coupling Internal Yield	psi	13,960	96,250
Internal Yield of Joint	psi	11,670	80,460

Coupling Color Code Coupling Color Code for the Band Pipe Color Code Identification

Additional Color Band (approx.10' from box end)

Note:

Band(s)	Red
	One Brown
	One Red, One Brown
	White

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

2"

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.