



CASING TECHNICAL DATA SHEET
5.5 x 0.361 HPP110 GBCD EHTQ

Reviewed by: Sr. Quality Engineer
Approved by: Corporate Director-QEHS

TDS Date (MM/DD/YY) 7/8/24

PIPE BODY DATA

Nominal Outside Diameter
Nominal Wall Thickness
Remaining Body Wall (RBW)
Type of Thread
Grade

Label Weight
Plain End Weight
Pipe Minimum Yield
Pipe Maximum Yield
Pipe Minimum Tensile
Standard Drift Diameter (min)
Alternate Drift Diameter (min)
Pipe Body Plain End Yield
Pipe Body Internal Yield
Collapse Pressure - Standard
Collapse Pressure - High

CONNECTION DATA

Coupling Minimum Yield
Coupling Maximum Yield
Coupling Minimum Tensile
Coupling or Joint Outside Diameter (nom)
Coupling Thread Fracture Strength
Pipe Thread Fracture Strength
Pull Out Strength
Nominal Make-Up Torque or Make-up Torque Range
Coupling Internal Yield
Internal Yield of Joint

WELEDDED TUBE GENERAL INPUT CRITERIA

Coupling Color Code
Coupling Color Code for the Band
Pipe Color Code Identification
Additional Color Band (approx.10' from box end)

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.

Unit	Imperial	Metric	Unit
in	5.500	139.70	mm
in	0.361	9.17	mm
	95.0%	95.0%	
	GBCD EHTQ	GBCD EHTQ	
	HPP110	HPP110	
	20.00	20.00	
lb/ft	19.83	29.52	kg/m
ksi	125	862	MPa
ksi	140	965	MPa
ksi	125	862	MPa
in	4.653	118.18	mm
in	N/A	N/A	mm
lb	729,000	330,670	kg
psi	15,590	107,490	kPa
psi	N/A	N/A	kPa
psi	13,340	91,980	kPa

ksi	See Next Page	See Next Page	MPa
ksi	See Next Page	See Next Page	MPa
ksi	See Next Page	See Next Page	MPa
in	See Next Page	See Next Page	mm
lb	See Next Page	See Next Page	kg
lb	See Next Page	See Next Page	kg
lb	See Next Page	See Next Page	kg
ft-lb	See Next Page	See Next Page	N-m
psi	See Next Page	See Next Page	kPa
psi	See Next Page	See Next Page	kPa

2" Band(s)

White
One Teal
One White
Orange

GB Connection Performance Properties Sheet

Rev. 1 (07/05/2023)

ENGINEERING THE RIGHT CONNECTIONS

Casing: 5.5 OD, 20 ppf
Casing Grade**: WTC HP P110 (95% RBW)

Connection: GB CD EHTQ 6.300
Coupling Grade: API P-110

PIPE BODY GEOMETRY					
Nominal OD (in.)	5 1/2	Wall Thickness (in.)	0.361	Drift Diameter (in.)	4.653
Nominal Weight (ppf)	20.00	Nominal ID (in.)	4.778	API Alternate Drift Dia. (in.)	N/A
Plain End Weight (ppf)	19.83	Plain End Area (in. ²)	5.828		

PIPE BODY PERFORMANCE**					
Material Specification	WTC HP P110 (95% RBW)	Min. Yield Str. (psi)	125,000	Min. Ultimate Str. (psi)	125,000
Collapse		Tension		Pressure	
API (psi)	12,080	Pl. End Yield Str. (kips)	729	Min. Int. Yield Press. ** (psi)	15,590
High Collapse** (psi)	13,340	Torque		Bending	
		Yield Torque (ft-lbs)	84,570	Build Rate to Yield (°/100 ft)	104.2

GB CD EHTQ 6.300 COUPLING GEOMETRY			
Coupling OD (in.)	6.300	Makeup Loss (in.)	4.1250
Coupling Length (in.)	8.250	Critical Cross-Sect. (in. ²)	8.527

GB CD EHTQ 6.300 CONNECTION PERFORMANCE RATINGS/EFFICIENCIES					
Material Specification	API P-110	Min. Yield Str. (psi)	110,000	Min. Ultimate Str. (psi)	125,000
Tension		Efficiency		Bending	
Thread Str. (kips)	685	Internal Pressure (%)	100%	Build Rate to Yield (°/100 ft)	80.0
Min. Tension Yield (kips)	891	External Pressure (%)	100%	Yield Torque	
Min. Tension Ult. (kips)	1,013	Tension (%)	100%	Yield Torque (ft-lbs)	37,330
Joint Str. (kips)	685	Compression (%)	100%		
		Ratio of Areas (Cplg/Pipe)	1.46		

MAKEUP TORQUE					
Min. MU Tq. (ft-lbs)	10,000	Max. MU Tq. (ft-lbs)	20,000	Running Tq. (ft-lbs)	See GBC RP
				Max. Operating Tq. (ft-lbs)*	35,460

Units: US Customary (lbm, in., °F, lbf)

1 kip = 1,000 lbs

* See Running Procedure for description and limitations.

See attached: Notes for GB Connection Performance Properties.

GBC Running Procedure (GBC RP): www.gbconnections.com/pdf/RP-GB-DWC-Connections.pdf

Blanking Dimensions: www.gbconnections.com/pdf/GB-DWC-Blanking-Dimensions.pdf

Connection yield torque rating based on physical testing or extrapolation therefrom

** Casing properties applicable to WTC HP P110 (95% RBW) grade with min. yield 125 ksi.