Welded Tube
Fueling Growth, Shaping Futures

CASING TECHNICAL DATA SHEET
9.625 x 0.395 HPP110 Long Round

Reviewed by: Sr. Quality Engineer
Approved by: Corporate Director-QEHS

TDS Date (MM/DD/YY) 11-11-26

PIPE BODY DATA	Unit	Imperial	Metric	Unit
Nominal Outside Diameter	in	9.625	244.48	mm
Nominal Wall Thickness	in	0.395	10.03	mm
Remaining Body Wall (RBW)		95.0%	95.0%	
Type of Thread		Long Round	Long Round	
Grade		HPP110	HPP110	
Coupling Type		11th Edition	11th Edition	
Label Weight		40.00	59.53	
Plain End Weight	lb/ft	38.97	57.99	kg/m
Pipe Minimum Yield	ksi	125	862	MPa
Pipe Maximum Yield	ksi	140	965	MPa
Pipe Minimum Tensile	ksi	125	862	MPa
Standard Drift Diameter (min)	in	8.679	220.45	mm
Alternate Drift Diameter (min)	in	8.750	222.25	mm
Pipe Body Plain End Yield	lb	1,432,000	649,540	kg
Pipe Body Internal Yield	psi	9,750	67,220	kPa
Collapse Pressure - Standard	psi	N/A	N/A	kPa
Collapse Pressure - High	psi	3,650	25,170	kPa

CONNECTION DATA				
Coupling Minimum Yield	ksi	110	758	MPa
Coupling Maximum Yield	ksi	140	965	MPa
Coupling Minimum Tensile	ksi	125	862	MPa
Coupling or Joint Outside Diameter (nom)	in	10.625	269.88	mm
Coupling Thread Fracture Strength	lb	2,389,000	1,083,630	kg
Pipe Thread Fracture Strength	lb	1,106,000	501,670	kg
Pull Out Strength	lb	1,087,000	493,050	kg
Nominal Make-Up Torque or Make-up Torque Range	ft-lb	10,870	14,740	N-m
Coupling Internal Yield	psi	13,280	91,560	kPa
Internal Yield of Joint	psi	9,750	67,220	kPa

WELDED TUBE GENERAL INPUT CRITERIA		
Coupling Color Code		White
Coupling Color Code for the Band		None
Pipe Color Code Identification	2" Band(s)	One White
Additional Color Band (approx.10' from box end)		Orange

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application. Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.